

TECHNICAL DATA SHEET

⊕ www.kimiajavidco.com
⋈ info@kimiajavidco.com
⊕ k i m i a j a v i d c o
♦ + 9 8 2 1 - 9 1 0 1 0 3 2 3
♠ No. 24-Mir St-Feiz square-Isfahan-Iran

Kimcross 1505

Polyethylene adhesive resin

Product Description

Kimcross 1505 is an anhydride-modified polyethylene acts as an adhesion promoter, which is designed for adhesion between PE and PA or EVOH in blown and cast film and especially double-bubble applications. Functionality of this polymer also promotes adhesion between metal, polyolefins, cellulose, polyester, polycarbonate, glass, and foil.

Main Characteristics:

Excellent adhesion of polyethylene to polyamide and EVOH.

General						
Features		Adhesion Durability	· Good Adhesion		· Excellent Process ability	
Uses	•	Multilayer Packaging				
Appearance		Natural				
Forms	•	Pellets				
Packaging		25 sacks				
Processing Method	•	Extrusion				
Food contact approval	•	Yes				
Physical			Nominal Value	Unit	Test Method	
Density			0.925 ± 0.005	g/cm³	ISO 1183	
Melt Mass-Flow Rate (190 °C /2.16 kg)			2.0 ± 0.5	g/10 min	ISO 1133	
Oxidation Induction Time (210 °C)			>30	min	ISO 11357	
Water content			< 0.1	%	ISO 15512	
Mechanical			Nominal Value	Unit	Test Method	
Tensile Stress (Break)			> 24	MPa	ISO 527	
Tensile Stress (Yield)			>12	MPa	ISO 527	
Tensile Strain (Break)			> 600	%	ISO 527	
Thermal			Nominal Value	Unit	Test Method	
Vicat Softening Temperature			105	°C	ISO 306/A50	
Melt Temperature			125	°C	ISO 3146	
Hardness			Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)			46±2	-	ISO 868	
Extrucion						

Extrusion

As a guide the following temperature profile is recommended:

Zone 1	Zone 2	Zone 3	Zone 4	Head	Die	Melt Temp
150	160	170	180	185	195	210-230

Shelf life

Sacks should be stored in dry/closed condition at temperature below 50 °C and protected from UV /direct sunlight. Shelf life at proper storage is at least 18 months from production date, but in case of a long storage time potential moisture pick-up needs to be eliminated by drying before extrusion.

Note

- Test results have been achieved in lab condition. Miss handling may give different result and sometimes outside of the standard
- The specifications given are the guidelines only.
- Above compound is suitable to run on different machines; however, some adjustments may be required on individual machine.
- The customers are advised to check the quality, prior to commercial use. There is no guarantee and/or warrantee what so ever, after processing.

Issue Date: May. 2023 Issue Number: 01 R&D Department