



Kimalloy 3320

Polybutylene terephthalate Alloy

Product Description

Kimalloy 3320 is a polymeric alloy of Poly (butylene terephthalate) and Poly (ethylene terephthalate). This product offers good surface appearance, good flow, low shrinkage percent and excellent heat resistance. This grade is especially suitable for metallizing applications.

Applications:

Automotive parts, Household parts

General

Material Status	• Commercial: Active		
Availability	• Middle East, Asia		
Features	• Good process ability	• Metallizable grade	
Uses	• Automotive parts	• Household parts	
Forms	• Pellets		
Color	• Black		
Packaging	• 25 kg PE bag		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40 ± 0.04	-	ISO 1183

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (yield)	60 ± 2	MPa	ISO 527
Tensile Modulus	2200 ± 100	MPa	ISO 527
Tensile Strain (Break)	> 50	%	ISO 527
Charpy unnotched Impact Strength at 23°C	> 35	kJ/m ²	ISO 179
Charpy notched Impact Strength at 23°C	> 3	kJ/m ²	ISO 179

Injection

As a guide the following temperature profile and other condition is recommended

Zone 1	Zone 2	Zone 3	Zone 4	Die	Mold Temperature
230-240°C	240-250°C	240-250°C	250-255°C	250-255°C	60-70°C
Drying Temperature			Drying Time		
90-100 °C			1-2 hr.		

Storage & Shelf Life

Sacks should be stored in dry/closed condition and protect from sunlight.

Shelf life at proper storage is at least 24 months from production date, but in case of a long storage time, potential moisture pick-up needs to be eliminated by drying before injection.

Note

- Test results have been achieved in lab condition. Miss handling may give different result and sometimes outside of the standard
- The specifications given are the guidelines only.
- Above compound is suitable to run on different machines; however some adjustments may be required on individual machine.
- The customers are advised to check the quality, prior to commercial use. There is no guarantee and/or warrantee what so ever, after processing

Issue Date: Nov. 2019

Issue Number: 01

R&D Department