



# TECHNICAL DATA SHEET

KIMIA JAVID SEPAHAN Co.

Newpipe Building, No. 83, Dr. Shariati Street (West), Tohid Ave, Isfahan, Iran

Phone: +98(31)-36937 (Ext 7281-7282)

Fax: +98(31)-62822010 Post Code: 817387685

Email : info@kimiajavid.ir

www.kimiajavidco.com

## Kimcol 5857

Black Masterbatch

### Product Description

Kimcol 5857 is designed for general purpose film, sheet extrusion and moulding applications. The amount of masterbatch added depends on the performance requirements of the final application and the carbon black content specified in the finished product.

Typical addition rates vary from 2% to 6% masterbatch.

### General

Carrier	• PE
Pigment	• CB
Compatibility	• LDPE, LLDPE, HDPE
Forms	• Pellets
Packaging	• 25 Kg PE Bag

Physical	Nominal Value Unit	Test method
MFR(190°C – 21.6Kg)	38±6 g/10min	ASTM D 1238
Ash Content (600°C)	<0.6	ASTM D 5630
Carbon black content	44±1	ASTM D 1603
Moisture Content	<1500 ppm	ASTM D 6980

### Storage

Kimcol 5857 is supplied in pellet form packed in 25 kg composite bags. Kimcol 5857 should be stored in a dry place. Under these conditions the product can be hold at least 24 months.

### Note

- Test results have been achieved in lab condition. Miss handling may give different result and sometimes outside of the standard
- The specifications given are the guidelines only.
- Above compound is suitable to run on different machines; however some adjustments may be required on individual machine.
- The customers are advised to check the quality, prior to commercial use. There is no guarantee and/or warrantee what so ever, after processing

Issue Date: AUG. 2020

Issue Number: 02

R&D Department