



TECHNICAL DATA SHEET

KIMIA JAVID SEPAHAN Co.

Newpipe Building, No. 83, Dr. Shariati Street (West), Tohid Ave, Isfahan, Iran

Phone: +98(31)-36937 (Ext 7281-7282)

Fax: +98(31)-62822010 Post Code: 817387685

Email : info@kimiajavid.ir

www.kimiajavidco.com

Kimfill 4526

Reinforced Polyamide 66 Compound

Product Description

Kimfill 4526 is a 25% chemically coupled glass fiber reinforced polyamide 66 compound developed especially for demanding applications in various engineering sectors. Kimfill 4526 has good properties such as stiffness, strength, hardness, dimensional stability, thermal and creep resistance, and reduced shrinkage.

General

Material Status	• Commercial: Active
Availability	• Middle East, Europe, Asia
Additive	• 25% Filler by Weight(Glass Fiber), Heat Stabilizer
Features	• Good Surface Finish • High Heat Stability • Good Process Ability
Uses	• Automotive • Electronic, Electrical Appliance • Household and Industrial Parts
Appearance & Form	• Black, Pellet
Packaging	• 25 Kg Multi-Layer Bag
Processing Method	• Injection Molding

Nominal Value Unit

Test Method

Physical

Density	1.29±0.01 g/cm ³	ISO 1183
Filler Content	25±2 %	ISO 3451-1

Mechanical

Tensile Modulus	7500 MPa	ISO 527
Tensile Strength (5mm/min)	145±5 MPa	ISO 527
Tensile Strain (Break)	4-5 %	ISO 527
Charpy Unnotched Impact Strength (23°C)	≥ 55 KJ/m ²	ISO 179

Processing Conditions

As a guide the following temperature profile and other condition is recommended

Zone 1	Zone 2	Zone 3	Zone 4	Die	Drying Time	Drying Temperature
270-280°C	280-285°C	285-290°C	285-295°C	290-295°C	2-4 hr.	90-100 °C

Shelf Life & Storage

Shelf life at proper storage is at least 18 months from production date, but in case of a long storage time, potential moisture pick-up needs to be eliminated by drying before injection. Sacks should be stored in dry/closed condition and protect from sunlight.

Note

This documentation is made out based on our tests and experiments in our R&D center with piled up experience and knowledge. And the values are measured on injection molded test specimens. It is suggested that this information contained in this document can be used for general indication. Therefore, you should not construe it as product specifications, and you should do appropriate test before you considering your conditions for newly applications.

Issue Date: Nov. 2019

Issue Number: 01

R&D Department